

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
30 October 2003 (30.10.2003)

PCT

(10) International Publication Number
WO 03/089218 A1

(51) International Patent Classification⁷: **B29C 41/02**,
71/00, 71/02, G06F 17/50, 19/00

(21) International Application Number: PCT/US03/10220

(22) International Filing Date: 4 April 2003 (04.04.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/373,186 17 April 2002 (17.04.2002) US

(71) Applicant (for all designated States except US): **STRATASYS, INC.** [US/US]; 14950 Martin Drive, Eden Prairie, MN 55344-2020 (US).

(71) Applicants and

(72) Inventors (for US only): **PRIEDEMAN, JR., William,**

R. [US/US]; c/o STRATASYS, INC., 14950 Martin Drive, Eden Prairie, MN 55344-2020 (US); **SMITH, David, Thomas** [US/US]; c/o STRATASYS, INC., 14950 Martin Drive, Eden Prairie, MN 55344-2020 (US).


(74) Agents: **CHAPMAN, Gena, M. et al.; KINNEY & LANGE, PA**, Kinney & Lange Building, 312 South Third Street, Minneapolis, MN 55415-1002 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),

[Continued on next page]

(54) Title: SMOOTHING METHOD FOR LAYERED DEPOSITION MODELING



(57) Abstract: Disclosed is a method for smoothing the surface of an object built from a polymeric or wax material using a layered manufacturing rapid prototyping technique. After the object is built it is exposed to a vaporized solvent such as in a vaporizer for an exposure time sufficient to reflow the object surface. A solvent is chosen based on its ability to transiently soften the material which forms the object, and thereafter evaporate off the object. The object is removed from the solvent and allowed to dry, producing a smooth finished part.



WO 03/089218 A1